

Fabrication of Photonic Bandgap Structures

Yong-Kee Yeo

gtg656i@mail.gatech.edu

Department of ECE, Georgia Tech



Outline


- Photonic Bandgap (PBG) concept and applications
- Fabrication of 2D PBG structure
- 3D PBG structures and fabrication techniques
- Conclusions




Photonic Bandgap Structures

Photonic Band Gap structures are periodic dielectric structures that forbid propagation of Electromagnetic waves in a certain frequency range

- First postulated by E. Yablonovitch in 1987
- Analogous to semiconductor bandgap
- PBG structures can be classified into 1 dimensional (used in DFB lasers and Fiber Bragg Gratings), 2 or 3-dimensional
- The bandgap is desired to be as large as possible so that it is less sensitive to fabrication-related disorders




Periodicity of dielectric constants




Fleming et al.




Application of PBG Structures




Highly miniaturized optical interconnects



Photonic Crystal Fibers (Holey Fibers)




Surface Plasmon LED




"Thresholdless" Nano-Cavity Lasers



Miniaturization of Opto-Digital Circuits



Typical Dimensions of PBG Structures



Some numbers (for triangular lattice) : $a=500\text{nm}$; $r=200\text{nm}$; $d=280\text{nm}$




2-Dimensional PBG Structures





SOI-based PBG WG Fabrication Procedure

1. Oxide deposition
2. Hydrofluoric acid dissolution to obtain desired thickness
3. Spin coat PMMA
4. Bake at 150degrees at 45min
5. E-Beam Lithography [30kV]
6. Develop PMMA in 2-ethoxyethanol and methanol for 30sec
7. Transfer pattern using Chemically Assisted Ion Beam Etching [1250V Ar⁺ beam with XeF₂]
8. Remove PMMA
9. Wafer thinning and cleaving
10. Undercutting using hydrofluoric acid



Photonic Nanocavity Laser




Light is localized through index guiding in the vertical direction and this results in significant radiation losses when the translational symmetry is broken




3-Dimensional PBG Structures




Crystal Structures with 3D Bandgap




Diamond



A7 - Rhombohedral Graphite



FCC




K.M. Ho et al.

Inverse Opal Structure




3D PMMA Template using X-Ray Lithography



X-rays exposure directions

$$d = t * \tan \alpha$$




- The first man-made PBG structure with complete photonic bandgap was experimentally demonstrated (using microwaves) in 1991
- XRL is ideal for generating the complex 3D structure due to its large depth of focus
- Soft contact printing used is used: mask is 20-40um away from PMMA resist (6um thick)
- Both mask and sample is rotated 120deg after each exposure
- The PMMA is developed and used as a template for various infilling materials:
 - Dielectric: Silicon Carbon Nitride, Titanium Dioxide
 - Metal: Copper




3D Dielectric and Metallic PBG Structures

G Feiertag *et al.*




3D structure from negative tone resist


Cuisin *et al.*



Completed PMMA template



TiO₂ used as filler






Electrodeposited copper used as filler

Shrinkage and small filling factor of the filler material resulted in non-uniform structures




Layer-by-Layer Fabrication




- 3D structure with omnidirectional bandgap
- Precise control of each layer and incorporation of defects and photonic devices is possible
- Alignment of layers is challenging due to requirements for offsetting holes laterally




Drilled Alternating Layer of 3D Crystals: DALPC




Periodic grooves are patterned by EBL and etched using RIE




RF bias sputtering of Si/SiO₂ layers




Patterning of SNR/PMGI bilayer for liftoff. 2nd EBL is performed. After developing the SNR resist the pattern is transferred to the PMGI by O₂ RIE



Ni Film is evaporated and unnecessary Ni is lifted off with underlying PMGI



Air holes are drilled with electron cyclotron resonance (ECR) etching



Completed structure

To obtain corrugated pattern, balance between sputter deposition, sputter etching and re-deposition is crucial

Kuramonchi *et al.*



Fabricated DALPC Samples




FIG. 4. SEM images of doubly patterned holes. The shift between two patterns corresponds to the alignment error in the EB exposing machine.





FIG. 7. Cross-sectional SEM image of a Si/SiO₂ DALPC sample after drilling by fluoride-based ECR etching.

- Shift in pattern caused by the alignment error of EB machine (alignment errors of 50-90nm by using the alignment mark patterns)
- The ECR plasma etching process is carried out with SF₆-CF₄-CO₂ gas (at pressures below 0.2mTorr)
- As a result of the low pressure, a 30W 400kHz RF bias is enough to accelerate ions for etching SiO₂ without increasing Fluorine radicals that will undercut Si
- Si undercut is also strongly suppressed by sidewall polymerization

Kuramonchi *et al.*




The WoodPile Structure and its Evolution



Ho et. al


Woodpile structure first Proposed in 1994. FCC lattice



Photonic Band Gap structure obtained by stacking Alumina rods. The gap is between 12 and 14 GHz.

Ozbay et. al

Alumina rods stacked and glued together; measurements are performed in mm-wave frequencies



Ref: S. Noda




<100μm

Zero-Threshold Laser Array

Integration of optical interconnects and active devices in same structure



Fabrication of WoodPile Structure





Final structure after oxide removal using HF




Alternate Fabrication Method


1. Patterning of stripes




2. Wafer stacked and fused in H_2 environment





3. One of the substrate and its etch stop layer chemically etched



4. Processes 2 & 3 repeated for every subsequent layer



Laser Beam ($\lambda_L = 0.98\mu m$)



- Layers are aligned using diffraction patterns formed by the gratings
- Samples with 8 layers operating in 1.3-1.55 μm region have been demonstrated



Conclusions

- Various high resolution microelectronic fabrication techniques were successfully used to produce 2D and 3D PBG structures which have been experimentally verified to possess photonic bandgaps in the infrared region
- Fabrication challenges and requirements:
 - Lattice constants comparable to wavelength of propagating light
 - High demand on uniformity and regularity of lattice structure
 - High anisotropy and selectivity requirements for high aspect ratio drilling
 - Layer-to-layer alignment must be very precise
 - Incorporation of active devices and defects into the structure



References

1. M. Loncar, D. Nedeljkovic, J. C. Cotteverte, T. Doll, A. Scherer, J. Gerretsen and T. P. Pearsal, "Waveguiding at 1500nm using Photonic Crystal Structures in Silicon on Insulator Wafer", CLEOS 2000
2. Yoel Fink, Augustine M. Urbas, Mouni G. Bawendi, John D. Joannopoulos and Edwin L. Thomas, "Block Copolymers as Photonic Bandgap Materials", J. Lightwave Tech., Vol 17, No. 11, Nov 1999, pp.1963-1969
3. J. R. Wendt, G. A. Vawter, P. L. Gourley, T. M. Brennan, and B. E. Hammons, "Nanofabrication of photonic lattice structures in GaAs/AlGaAs", J. of Vacuum Science B, Nov/Dec 1993, pp.2637-2640
4. Eiichi Kuramonchi, Masaya Notomi and Toshiaki Tamamura, Takayuki Kawashima, Shojiro Kawakami, Jun-ichi Takahasi and Chiharu Takahasi, "Drilled alternating-layer structure for three dimensional photonic crystals with a full band gap", J. Vac. Sci. Tech. B 18(6), Nov/Dec 2000, pp.3510-3513
5. W. D. Zhou, P. Bhattacharya, J. Sabarinathan, and D. H. Zhu, "Fabrication of GaAs-based photonic band gap materials", J. Vac. Sci Tech. B, 18(3), May/June 2000, pp. 1706-1710
6. C. Cuisin, A. Chelnokov, J. M. Lourtioz, D. Decanini and Y. Chen, "Fabrication of three dimensional photonic structures with sub-micrometer resolution by X-ray lithography", J. Vac. Sci. Tech. B, 18(6), Nov/Dec 2000, pp.3505-3509
7. Ganesh Subramania, "Thin Film Inverse Opal Photonic Crystals: Synthesis and Characterization", Iowa State University, AMES Lab
8. S. G. Johnson and J. D Joannopoulos, "Three-dimensional periodical dielectric layered structure with omnidirectional photonic band gap", Appl. Phys. Letters 77, Nov 2000, pp.3940-3942
9. E. Ozbay, A Abeyta, G Tuttle, M Tringides, R Biswas, C. T. Chan, C. M. Soukoulis and K. M. Ho, "Measurement in three dimensional photonic bandgap in a crystal structure made of dielectric rods", Physical Review B, Vol. 50, July 1994, pp.1945-1949
10. Susumu Noda, Noritsugu Yamamoto, Masahiro Imada, Hideaki Kobayashi and Makoto Okano, "Alignment and stacking of semiconductor photonic bandgaps by wafer fusion", Journal of Lightwave Tech., Vol. 17, Nov 1999, pp.1948-1955



References

11. J. G. Fleming and Shawn-Yu Lin, " Three dimensional photonic crystal with a stop band from 1.35 μm to 1.95 μm ", Optics Letters, Jan 1999, Vol. 24 No. 1, pp.49-51
12. G. Feiertag et al. , "Fabrication of Photonic Crystals by Deep X-Ray Lithography", Appl. Phy. Lett., 71, Sep 1997, pp.1441-1443
13. Axel Scherer, O. Painter, J. Vuckovic, M. Loncar, T. Yoshie, "Semiconductor Photonic Bandgap Structures", 2002
14. E. Yablanovitch, T. J. Gmitter and K. M. Leung, "Photonic Bandgap Structure: the face-centered-cubic case employing Non-spherical atoms", Physical Review Letters, Vol. 67, Oct. 1991, pp.2295-2299

